



**GVM TEST HOUSE
AND RESEARCH CENTRE**

Report No.: GVM:WPS: 01671-1/05/2022

Date of Receipt: 25.05.2022

ORBIT MARKETING SERVICES

208, Bldg No.8, Jogani Complex,

V.N. Purav Marg, Chunabhatti,

Sion(E), Mumbai 400022



AN ISO 9001-2015 CERTIFIED

Date: 08-06-2022

Page 1 of 1

TEST REPORT ON TRIMIX STARSHIELD CEMENTITIOUS WATERPROOFING COMPOUND

Source of sample : Sample Submitted by Customer
 Number of samples Tested : 01 (One Only)
 Condition of sample : Satisfactory
 Customer's Reference : Letter dated 25.05.2022
 Lab Reference Number : 2022/MAY/01671-1
 Material Identification # : Trimix Starshield Cementitious Waterproofing Compound
 Mixing Ratio # : Powder : Resin = 3 : 1
 Period of Test : 26.05.2022 To 08.06.2022
 Test Method : IS : 6582(Part 2) : 2001

TEST RESULTS:

1. Test Conditions Maintained:

Sr. No.	Parameter	Container Containing only Water	Container applied with Trimix Starshield Cementitious Waterproofing Compound Coating
1.	Temperature (°C ± 1)	27.0	27.0
2.	pH	7.21	7.38
3.	Dissolved Oxygen Immediate (mg/lit)	7.80	7.90
4.	Dissolved Oxygen After 24 Hours (mg/lit)	7.70	7.50
5.	Dissolved Oxygen After 48 hours (mg/lit)	7.60	7.40

2. Test Results:


Sr. No.	Mixing Ratio	Results
1.	Powder: Resin = 3 : 1	100% survival up to 96 hours.

Remarks: 1. Above aquatic toxicity of sample was carried out as per IS : 6582(Part 2) : 2001 on Zebra Fish.
 2. Trimix Starshield Cementitious Waterproofing Compound sample applied in 2 Coats as per above proportion on a Container & the container dried for 7 days & later filled with Fishes & Fresh Water.

As furnished by the customer.

Note: 1. The Results relate only to the samples tested.
 2. Report shall not be reproduced, except in full, without the written approval of the lab.
 3. Any correction invalidates this report.

For GVM Test House And Research Centre


DINESH BURDE

 GVM TEST HOUSE AND RESEARCH CENTRE
 Authorised Signatory



GVM Test House And Research Centre

Lab Add.: #23/24, Yashodeep Heights, Plot No. 14/15, Sector 29C, Rabale-Ghansoli Node, Navi Mumbai-400701 (India),
 Email : lab@gvmtesthouse.com Web.: www.gvmtesthouse.com, Mob: 9689891932.

Regd. Off.: 402, Yogesh Apartment CHS, Plot No. 26, Sector - 8A, Airoli, Navi Mumbai - 400708.

|Testing

|Training

|Auditing